

# Velair 89 Tailplain Spar Construction

Laminate construction of tailplain spar  
CIBA-GEIGY T300/920 unidirectional carbon fibre pre preg  
0.125mm cured ply thickness  
4 layers carbon at  $\pm 45^\circ$  on a 30mm diameter mandral  
2 20mm wide layers of carbon at  $0^\circ$

